



## FDI POLICY STATEMENT

### Intraoral Light Curing of Resin Based Material

To be adopted by the FDI General Assembly:  
27-29 September 2021, Sydney, Australia

1  
2

#### 3 **CONTEXT**

4 Light-cured direct resin-based materials (RBMs) and dental light-curing units (LCUs)  
5 have become ubiquitous in dental clinics worldwide. Recently, novel materials using  
6 alternative photoinitiators in addition to camphorquinone and new LCUs emitting  
7 different spectra of light have become available for clinical practice. In contrast to the  
8 broad emission spectrum of quartz-tungsten-halogen (QTH) lights, the emitted  
9 wavelength of some light-emitting diode (LED) LCUs or laser LCUs may be too narrow  
10 to activate all of the newer photosensitizers. Such physico-chemical incompatibility is  
11 concerning because the clinical success and the biocompatibility of RBMs (e.g. resin  
12 composites, adhesives, orthodontic resins, luting agents and sealants) depend on how  
13 thoroughly they are light-cured in the mouth.<sup>1,2</sup> This policy statement addresses this  
14 often unrecognized problem and provides timely recommendations for intraoral light-  
15 curing.

16

#### 17 **SCOPE**

18 This FDI Policy Statement highlights important aspects for the correct use of different  
19 LCUs (e.g. QTH, LED and Laser) in dental practice. It indicates that professional  
20 guidance and education on the appropriate use of LCUs ( e.g. the effects of tip position,  
21 movement, angulation and exposure time) are needed.<sup>1</sup>

22

#### 23 **DEFINITIONS<sup>1,3</sup>**

##### 24 **Radiant exitance (mW/cm<sup>2</sup>):**

25 Radiant power of electromagnetic radiation emitted by a surface per unit area.

26

##### 27 **Irradiance (mW/cm<sup>2</sup>):**

28 Radiant power of electromagnetic radiation received by a surface per unit area.

29 Note: the irradiance is measured at various distances from the source, and it equals  
30 exitance at 0 mm from the tip.

31

##### 32 **Emission spectrum (nm):**

33 Range of wavelengths of electromagnetic radiation emitted by the light source.

34

35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65  
66  
67  
68  
69  
70  
71  
72  
73  
74  
75  
76  
77  
78  
79  
80  
81  
82

**Spectral radiant power/Spectral flux (mW/nm):**

Radiant power of electromagnetic radiation emitted, transmitted, reflected, or received per unit wavelength.

**Light beam uniformity:**

Homogeneity of both the irradiance and spectral radiant power across the light beam from the light source.

**Photoinitiator:**

Chemical component of light-cured RBMs that, when activated by a specific wavelength of visible light, initiates the polymerization of the RBMs.

**Photosensitizer:**

Chemical component of a photoinitiator system that reacts with an accelerator to produce reactive species for polymerization of the RBMs. Note: Camphorquinone is very often used as a photosensitizer and an aliphatic amine is used as an accelerator.

**PRINCIPLES**

Long-term success of restorations depends on many factors. Adequate light curing is an important but commonly underestimated issue. The correct selection and use of intra-oral LCUs are essential for the safety of patients and operators as well as for the long-term success of direct dental restorations and other intraorally light-cured dental materials.<sup>1</sup> The safe use of LCUs requires appropriate eye-protection.

**POLICY**

According to ISO standards (10650:2018 and 4049:2019)<sup>4</sup>, manufacturers of light-curable dental materials should provide clear information on the specific wavelengths of light, irradiance, exposure time and the maximum thickness of the RBM for assuring sufficient light-curing. Furthermore, they should give clear information on characterizing the LCUs regarding emitted radiant power, radiant exitance, irradiance loss over distance, emission spectrum and active tip area, and display specifications on light transmission and beam uniformity. Manufacturers of both light-curable dental materials and LCUs need to provide data required by standardized test methods and meet standardized labelling and instructions of requirements for usage.<sup>5</sup>

FDI supports the following recommendations:

- Dental practitioners should check that the wavelengths of light emitted by the LCUs are used appropriately to those specified by the manufacturer of the RBMs.
- The maximum increment thickness of the material and the exposure time recommended by the manufacturer should be followed.
- Darker and/or more opaque colors/shades of the same product may require

83 longer exposure times and/or may need to be applied in smaller increment  
84 thicknesses.

85  
86 • The average radiant exitance of the LCUs should be in the range of 500 to 2000  
87 mW/cm<sup>2</sup>. Areas at the tip of the LCUs that emit a radiant exitance below 500  
88 mW/cm<sup>2</sup> may result in insufficient photocuring, and above 2000 mW/cm<sup>2</sup> may  
89 create thermal irritation and/or damage to oral tissues.<sup>5</sup> Care is required when  
90 using high output LCUs (above 2,000 mW/cm<sup>2</sup>) that advocate very short  
91 exposure times (1-5 seconds). Although some resin bonded composites  
92 (RBCs) are matched to certain high output LCUs with short curing-time, high  
93 output LCUs may not adequately cure all RBCs.

94  
95 • The performance of LCUs needs to be checked regularly as the radiant exitance,  
96 (i.e. irradiance at the light tip) may change over time. In addition, it is important  
97 that the unit is regularly charged and the tip is clean and aseptic.

98  
99 • Photocuring of resin materials also depends on the angulation of the light tip  
100 and distance from the light tip to the material.<sup>2,6</sup> In deep cavities, the exposure  
101 time should be prolonged to compensate for the loss of irradiance.

102  
103 • A standardized assessment is mandatory for the efficacy of devices to protect  
104 the clinician's eyes, either attached to an LCU, handheld or as protective  
105 goggles. Professional education on the appropriate use of LCUs (e.g. the effects  
106 of tip position, movement, or angulation) is needed.<sup>1,7</sup>

107  
108 • Dental practitioners should provide essential instruction and supervision when  
109 light-curing devices are used by other members of the dental team, and make  
110 sure that those personnel are trained appropriately and understand the  
111 principles and professional recommendations on light curing as described  
112 above.

113  
114 Further research on the safety and efficiency of LCUs and dental materials should be  
115 encouraged.

116

117 **KEYWORDS**

118 Light-curing unit, restorative materials, resin composite, light-curable, photo-  
119 polymerization, photoinitiator, LED LCU

120

121 **DISCLAIMER**

122 The information in this Policy Statement was based on the best scientific evidence  
123 available at the time. It may be interpreted to reflect prevailing cultural sensitivities  
124 and socio-economic constraints.

125

126

127 **REFERENCES**

- 128 1. Price RB, Ferracane JL, Shortall AC. Light-Curing Units: A Review of What We  
129 Need to Know. *J Dent Res.* 2015;94: 1179-86.  
130
- 131 2. Maktabi H, Ibrahim M, Alkhubaizi Q, et al. Underperforming light curing procedures  
132 trigger detrimental irradiance-dependent biofilm response on incrementally placed  
133 dental composites. *J Dent.* 2019;88: 103-110.  
134
- 135 3. Kirkpatrick SJ. A primer on radiometry. *Dent Mater.* 2005;21: 21-6.  
136
- 137 4. International Organization for Standardization. *Dentistry-Powered polymerization*  
138 *activators*. International Organization for Standardization ISO. Document number:  
139 10650:2018(en). Available from: <https://www.iso.org/standard/73302.html>  
140 [Accessed 27 November 2020].  
141
- 142 5. Park SH, Roulet JF, Heintze SD. Parameters influencing increase in pulp  
143 chamber temperature with light-curing devices: curing lights and pulpal flow rates.  
144 *Oper Dent.* 2010;35(3): 353-61.  
145
- 146 6. Konerding KL, Heyder M, Kranz S, et al. Study of energy transfer by different light-  
147 curing units into a class III restoration as a function of tilt angle and distance,  
148 using a MARC Patient Simulator (PS). *Dent Mater.* 2016;32: 676-86.  
149
- 150 7. Fluent MT, Ferracane JL, Mace JG, Shah AR, Price RB. Shedding light on a  
151 potential hazard: Dental light-curing units. *J Am Dent Assoc.* 2019;150: 1051-  
152 1058.  
153  
154